

PRODUCTION OF ANTIFUNGAL PAINTED METAL PANEL

Patent number: JP7313935
Publication date: 1995-12-05
Inventor: YANO HIROKAZU; UDAGAWA YOSHIKATSU; SAKAI TETSUO; FUKUMOTO HIROMITSU
Applicant: NISSHIN STEEL CO LTD
Classification:
- international: B05D5/00; B05D7/14; B05D7/24; B32B15/08; C09D5/14; B05D5/00; B05D7/14; B05D7/24; B32B15/08; C09D5/14; (IPC1-7): B05D7/24; B05D5/00; B05D7/14; B32B15/08; C09D5/14
- european:
Application number: JP19940136532 19940526
Priority number(s): JP19940136532 19940526

[Report a data error here](#)

Abstract of **JP7313935**
 PURPOSE:To keep antifungal effect long, in producing an antifungal painted metal panel by painting a metal panel with thermosetting paint to which an antibacterial agent and an antifugal agent are added by a specific ratio to bake and cure the paint layer, by compounding a melamine resin with the paint in a specific ratio. CONSTITUTION:Thermosetting paint having an antibacterial agent and an antifungal agent added thereto in an amt. of 0.1-50 pts.wt. per 100 pts.wt. of a paint solid is applied to a metal panel and baked and cured to produce an antifungal painted metal panel. In this case, 0.1-100 pts.wt. of a melamine resin curing agent is compounded with 100 pts.wt. of the paint solid. As the melamine resin curing agent, a methylated or butylated melamine resin is used. Since the compatibility of the melamine resin with a paint resin or a solvent is low, the melamine resin is conc. in a surface layer at the time of baking to form a dense layer and it is estimated that the elution of the antibacterial agent and the antifungal agent is suppressed by this layer. Therefore, a painted metal panel keeping antibacterial and antifungal effect long can be obtained.

.....
 Data supplied from the *esp@cenet* database - Worldwide